


PROCESS DETAILS

Process	EPITAXIAL PLANAR
Die Size	70 x 70 MILS
Die Thickness	9.0 MILS
Base Bonding Pad Area	11.4 x 18 MILS
Emitter Bonding Pad Area	13.7 x 23.6 MILS
Top Side Metalization	Al - 30,000Å
Back Side Metalization	Ti / Ni / Ag 11,300Å

GEOMETRY



BACKSIDE COLLECTOR

R1

GROSS DIE PER 4 INCH WAFER







2,200

PRINCIPAL DEVICE TYPES

CZT3120

145 Adams Avenue
Hauppauge, NY 11788 USA
Tel: (631) 435-1110
Fax: (631) 435-1824
www.centralsemi.com

R3 (26-March 2004)



145 Adams Avenue
Hauppauge, NY 11788 USA
Tel: (631) 435-1110
Fax: (631) 435-1824
www.centalsemi.com

R3 (26-March 2004)