

Data Sheet July 1999 File Number 4758

Radiation Hardened Triple 3-Input NOR Gate

The Radiation Hardened ACS27MS is a Triple 3-Input NOR Gate. For each gate, a HIGH level on any input results in a LOW level on the Y output. A LOW level on all inputs results in a HIGH level on the Y output. All inputs are buffered and the outputs are designed for balanced propagation delay and transition times.

The ACS27MS is fabricated on a CMOS Silicon on Sapphire (SOS) process, which provides an immunity to Single Event Latch-up and the capability of highly reliable performance in any radiation environment. These devices offer significant power reduction and faster performance when compared to ALSTTL types.

Specifications for Rad Hard QML devices are controlled by the Defense Supply Center in Columbus (DSCC). The SMD numbers listed below must be used when ordering.

Detailed Electrical Specifications for the ACS27MS are contained in SMD 5962-98630. A "hot-link" is provided on our homepage for downloading.

www.intersil.com/spacedefense/spaceselect.asp

Features

- QML Qualified Per MIL-PRF-38535 Requirements
- 1.25 Micron Radiation Hardened SOS CMOS
- Radiation Environment
 - Latch-Up Free Under Any Conditions
 - Total Dose (Max.) 3 x 10⁵ RAD(Si)
 - SEU Immunity.....<1 x 10⁻¹⁰ Errors/Bit/Day
 - SEU LET Threshold >100MeV/(mg/cm²)
- Input Logic Levels. . . . $V_{IL} = (0.3)(V_{CC}), V_{IH} = (0.7)(V_{CC})$
- Quiescent Supply Current 5.0μA (Max)


Applications


- · High Speed Control Circuits
- · Sensor Monitoring
- · Low Power Designs

Ordering Information

ORDERING NUMBER	INTERNAL MARKETING NUMBER	TEMP. RANGE (°C)	PACKAGE	DESIGNATOR
5962F9863001VCC	ACS27DMSR-03	-55 to 125	14 Ld SBDIP	CDIP2-T14
ACS27D/SAMPLE-03	ACS27D/SAMPLE-03	25	14 Ld SBDIP	CDIP2-T14
5962F9863001VXC	ACS27KMSR-03	-55 to 125	14 Ld Flatpack	CDFP3-F14
ACS27K/SAMPLE-03	ACS27K/SAMPLE-03	25	14 Ld Flatpack	CDFP3-F14
5962F9863001V9A	ACS27HMSR-03	25	Die	NA

Pinouts





Die Characteristics

DIE DIMENSIONS:

Size: $2390\mu m \times 2390\mu m$ (94 mils x 94 mils) Thickness: $525\mu m \pm 25\mu m$ (20.6 mils ± 1 mil) Bond Pad: $110\mu m \times 110\mu m$ (4.3 x 4.3 mils)

METALLIZATION: AI

Metal 1 Thickness: $0.7\mu m \pm 0.1\mu m$ Metal 2 Thickness: $1.0\mu m \pm 0.1\mu m$

SUBSTRATE POTENTIAL

Unbiased Insulator

PASSIVATION:

Type: Phosphorous Silicon Glass (PSG)

Thickness: $1.30\mu m \pm 0.15\mu m$

SPECIAL INSTRUCTIONS


Bond V_{CC} First

ADDITIONAL INFORMATION:

Worst Case Current Density: <2.0 x 10⁵ A/cm²

Transistor Count: 97

Metallization Mask Layout



All Intersil semiconductor products are manufactured, assembled and tested under ISO9000 quality systems certification.

Intersil semiconductor products are sold by description only. Intersil Corporation reserves the right to make changes in circuit design and/or specifications at any time without notice. Accordingly, the reader is cautioned to verify that data sheets are current before placing orders. Information furnished by Intersil is believed to be accurate and reliable. However, no responsibility is assumed by Intersil or its subsidiaries for its use; nor for any infringements of patents or other rights of third parties which may result from its use. No license is granted by implication or otherwise under any patent or patent rights of Intersil or its subsidiaries.

For information regarding Intersil Corporation and its products, see web site www.intersil.com

Sales Office Headquarters

NORTH AMERICA

Intersil Corporation
P. O. Box 883, Mail Stop 53-204
Melbourne, FL 32902
TEL: (321) 724-7000

TEL: (321) 724-7000 FAX: (321) 724-7240

EUROPE

Intersil SA Mercure Center 100, Rue de la Fusee 1130 Brussels, Belgium TEL: (32) 2.724.2111 FAX: (32) 2.724.22.05

ASIA

Intersil (Taiwan) Ltd. 7F-6, No. 101 Fu Hsing North Road Taipei, Taiwan Republic of China TEL: (886) 2 2716 9310 FAX: (886) 2 2715 3029