


PROCESS CP324
Small Signal MOSFET Transistor
N-Channel Enhancement-Mode Transistor Chip

CentralTM
Semiconductor Corp.

PROCESS DETAILS

Process	EPITAXIAL PLANAR
Die Size	21.65 x 21.65 MILS
Die Thickness	9.0 MILS
Gate Bonding Pad Area	5.5 x 5.5 MILS
Source Bonding Pad Area	5.9 x 13.8 MILS
Top Side Metalization	Al - 30,000Å
Back Side Metalization	Au - 12,000Å

GEOMETRY



BACKSIDE DRAIN R0

GROSS DIE PER 5 INCH WAFER






35,900

PRINCIPAL DEVICE TYPES

2N7002

145 Adams Avenue
Hauppauge, NY 11788 USA
Tel: (631) 435-1110
Fax: (631) 435-1824
www.centalsemi.com

R1 (1-August 2002)



145 Adams Avenue
Hauppauge, NY 11788 USA
Tel: (631) 435-1110
Fax: (631) 435-1824
www.centrasemi.com

R1 (1-August 2002)